



Alro Plastics

Your Source for Engineering Plastics

Sheet • Rod • Tube • Film • Profiles • Machined Parts

KING FLAME SHIELD

Upgrade to King FlameShield ASTM E-84 class A or class B flame compliance and CAN/ULC-S102 for Canadian compliance.

Properties	Units	ASTM	Value		
Density	g/cc	D1505	1.30 - 1.35		
Tensile Strength @ Break	psi	D638	1,170		
Tensile Strength @ Yield	psi	D638	3,780		
Elongation @ Break	%	D638	>300		
Elongation @ Yield	%	D638	8.6		
Flexural Modulus	psi	D790	179,000		
Flexural Stress @ 5% Strain	psi	D790	4,330		
Durometer	Shore D	D2240	71		
Tensile Impact	ft.lbs./in.2	D1822	99		
Vicat Softening	°C (°F)	D1525	129°C (264°F)		
Heat Deflection Temp. 66 psi	°C (°F)	D648	86.6°C (188°F)		
Thermal Expansion	---		Class A	Class B	
Surface Burning Characteristics	---	E84	20 & 60	60 & 450	FSI & SDO
Surface Burning Characteristics		ULC-S102	20 & 65	60 & 450	FSI & SDI

All values are determined on specimens prepared according to ASTM Standards.

Nominal values should be interpreted as specifications.

Tolerance Information:

Please refer to specific product information

Disclaimer: FlameShield may affect finish and color

* Please note King FlameShield additive will not affect the physical properties of the material.