



Alro Plastics

Your Source for Engineering Plastics

Sheet • Rod • Tube • Film • Profiles • Machined Parts

Acculam® Epoxyglas G11 non FR

Technical Data Sheet

Typical Properties	Typical Value	Units
Physical Data		
Specific Gravity/Density	1.85	g/cm ³
Water Absorption - .125"	< .10	%
Temperature Index	180 / 356	°C / °F
Rockwell Hardness	115	M scale
Bond Strength	2,200 / 1,000	lbs / kgs
Flexural Strength - LW - A	75,000 / 520	PSI / MPa
Flexural Strength - LW - E - 1/150	40,000 / 280	PSI / MPa
Izod Impact Strength - LW	> 10	ft-lbs/in
Izod Impact Strength - CW	> 8	ft-lbs/in
Compressive Strength - Flatwise	> 65,000 / 448	PSI / MPa
Electrical Data		
Dielectric Breakdown - A	> 50	kV
Dielectric Breakdown - D48/50	> 50	kV
Permittivity - A	4.8	
Permittivity - D24/23	4.8	
Dissipation Factor - A	0.017	
Dissipation Factor - D24/23	0.018	

Accurate provides this data as information only and does not imply any warranty for its use or application.

Product Description: Acculam® Epoxyglas G11 nonFR -Laminate sheet comprised of heat resistant/ halogen free epoxy resin and a woven fiberglass substrate. It qualifies to NEMA G11 and MIL-I-24768/3.

Typical Applications: This material exhibits extremely high mechanical strength at elevated temperatures and has good dielectric loss and electric strength properties under both dry and humid conditions. It is resistant to flow, dimensional change, chemicals and has low moisture absorption.