



## Nylatron GS (Quadrant)

Extruded nylon, type 6/6, MoS2 filled

Physical Properties	Metric	English	Comments
Specific Gravity	1.16 g/cc	0.0419 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.3 %	0.3 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	7 %	7 %	Immersion; ASTM D570 (2)

### Mechanical Properties

Hardness, Rockwell M	85	85	ASTM D785
Hardness, Rockwell R	115	115	ASTM D785
Hardness, Shore D	85	85	ASTM D2240
Tensile Strength, Ultimate	86.2 MPa	12500 psi	ASTM D638
Elongation at Break	25 %	25 %	ASTM D638
Tensile Modulus	3.31 GPa	480 ksi	ASTM D638
Flexural Modulus	3.17 GPa	460 ksi	ASTM D790
Flexural Yield Strength	117 MPa	17000 psi	ASTM D790
Compressive Strength	110 MPa	16000 psi	10% Def.; ASTM D695
Compressive Modulus	2.9 GPa	420 ksi	ASTM D695
Shear Strength	72.4 MPa	10500 psi	ASTM D732
Coefficient of Friction	0.2	0.2	Dry vs. Steel; QTM55007
K (wear) Factor	181 x 10 <sup>-8</sup> mm <sup>3</sup> /N-M	90 x 10 <sup>-10</sup> in <sup>3</sup> -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.105 MPa-m/sec	3000 psi-ft/min	4:1 safety factor; QTM 55007
Izod Impact, Notched	0.267 J/cm	0.5 ft-lb/in	ASTM D256 Type A

### Electrical Properties

Surface Resistivity per Square	Min 1e+013 ohm	Min 1e+013 ohm	EOS/ESD S11.11
Dielectric Strength	13.8 kV/mm	350 V/mil	Short Term; ASTM D149

### Thermal Properties

CTE, linear 68°F	72 µm/m-°C	40 µin/in-°F	(-40°F to 300°F); ASTM E831
Thermal Conductivity	0.245 W/m-K	1.7 BTU-in/hr-ft <sup>2</sup> -°F	ASTM F433
Melting Point	260 °C	500 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	104 °C	220 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	93.3 °C	200 °F	ASTM D648
Flammability, UL94 (Estimated Rating)	V-2	V-2	1/8 inch

### Qualitative Processing Properties

Compliance - FDA	Not Compliant		
Machinability	1	1-10, 1=Easier to Machine	
Service in Alcohols	Limited		
Service in Aliphatic Hydrocarbons	Acceptable		
Service in Aromatic Hydrocarbons	Acceptable		
Service in Chlorinated Solvents	Limited		
Service in Ethers	Acceptable		
Service in Ketones	Acceptable		
Service in Strong Acids	Unacceptable		
Service in Strong Alkalies	Unacceptable		
Service in Sunlight	Limited		
Service in Weak Acids	Limited		
Service in Weak Alkalies	Limited		

All statements, technical information and recommendations contained in this database are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that Quadrant EPP and Automation Creations, Inc. cannot guarantee the accuracy or completeness of this information, and it is the customer's responsibility to determine the suitability of Quadrant EPP's products in any given application.