



# King StarBoard

The original marine grade high density polyethylene

Tolerances	
Gauges	Width/Length
1/4" - 1 1/2" ± 5%	Plus Only at Room Temp.

Properties	Units	ASTM	Nominal Value*
Density	g/cc	D1505	.96
Tensile Strength @ Yield	p.s.i.	D638	>4100
Elongation @ Break	%	D638	>600
Flexual Modulus	p.s.i.	D790	185,000
Durometer	Shore D	D2240	68
Tensile Strength	ft. lbs./in. <sup>2</sup>	D1822	115
Brittleness Temp.	°C	D746	<-76
Vicat Softening	°C	D1525	123
Heat Deflection Temp. 66p.s.i.	°C	D648	75
Co-efficient of Linear Thermal Expansion	in//in./°F	D696	6x10 <sup>-5</sup>

\*All values are dtermined on specimens prepared accordeing for ASTM D4976. Nominal values should not be interpreted as specifications.

King StarBoard® is made entirely from FDA and USDA approved materials.

King Plastic Corporation (KPC) makes no representations or warranties and there are no conditions with respect to accuracy, reliability, or application of the information herein, its products or the safety or suitability thereof, or results obtained, whether expressed or implied including, without limitation, any implied warranty of merchantability of fitness for a particular purpose. Buyers and users must determine the results to be obtained from the application of the information herein and the safety and suitability of KPC's products for their own purposes and assume all risk, responsibility, and liability for all injuries, losses, or damages arising from the application of the information herein or use of KPC's products, whether or not occasioned by KPC's negligence or based on strict product liability. KPC neither assumes nor authorizes any person to assume for it any liability in connection with the use of the information herein or its products.