



# Stainless Steel

## Bar, Sheet, Plate, Structural, Tube & Pipe

**Technical Data & Applications** .....5-2 thru 5-13

**Stainless Rounds** ..... 5-14

**Stainless Half-Rounds** ..... 5-14

**Stainless Squares** ..... 5-15

**Stainless Hexagons** ..... 5-15

**Stainless Flats** ..... 5-16

**Stainless Sheets** ..... 5-17 thru 5-18

**Stainless Plate** ..... 5-19

**Stainless Angle** ..... 5-20

**Stainless Channel** ..... 5-21

**Stainless Beams** ..... 5-22

**Stainless Ornamental Tubing** ..... 5-22 thru 5-23

**Stainless Round Tube** ..... 5-24

**Stainless Welded Pipe** ..... 5-25

**Tolerances** ..... 5-26 thru 5-30

## Grade 201

201 alloy is a high performance austenitic stainless steel formulated to have a lower and more stable cost due to the substitution of manganese for a portion of the nickel used in 300 series stainless steels such as Type 304. In addition, the chemical composition of alloy 201 provides higher annealed mechanical properties than type 304 which can result in an additional benefit of weight reduction. The 201 tensile strength is about 10% higher than Type 304 which may allow for thinner gauges and therefore less material. However, due to the lower Chromium and Nickel content, Type 201 stainless may not have the same corrosion resistance as Type 304.

### Typical Applications

Commercial and residential food service applications, architectural end uses such as handrails and support frame work, washing machines, hose clamps, sinks, containers and structural components of truck trailers and railcars.

Typical Analysis	201
Chrome	16.00 - 18.00
Nickel	3.50 - 5.50
Carbon	.15 max.
Manganese	5.50 - 7.50
Silicon	1.00 max.
Sulphur	.030 max.
Phosphorus	.060 max.
Nitrogen	.250 max.
Iron	Balance
<b>Mechanical Properties</b>	<b>(Annealed)</b>
Brinell Hardness	175
Tensile—KSI	105
Yield—KSI	45
Elongation in 2"—%	58
Red. in Area—% Min	88
<b>Welding Characteristics</b>	Very good
<b>Machining</b>	
Compared to B1112 Screw Stock	45%
<b>Specifications</b>	<b>201 (Sheet)</b>
ASTM	A240

## Grade 303

303 is a free-machining variation of 304. The addition of sulfur for better machinability makes this a favorite for use in automatic screw machines. Corrosion resistant to atmospheric exposures, as well as a wide range of chemicals; most dyes, foods and nitric acid.

### Typical Applications

Bolts, bushings, nuts, shafts, and parts produced on automatic screw machines.

Typical Analysis	303/303 G&P
Chrome	17.0-19.0
Nickel	8.0 - 10.0
Carbon	.15 max.
Manganese	2.00 max.
Silicon	1.00 max.
Molybdenum	.60 max.
Sulphur	.15 min.
<b>Mechanical Properties</b>	<b>(Annealed)</b>
Brinell Hardness	160
Tensile—KSI	90
Yield—KSI	35
Elongation in 2"—%	50
Red. in Area—% Min	55
<b>Welding Characteristics</b>	Fusion welding not recommended
<b>Machining</b> Compared to B1112 Screw Stock	70%
<b>Specifications</b>	<b>303 (Bar)</b>
AISI	303
ASTM	A581, A582
AMS	5640

## Grade 304/304L

The most widely used of the austenitic grades, 304 offers good corrosion resistance to many chemicals and industrial atmospheres. Generally considered non-magnetic, it can become slightly magnetic when cold-worked. 304 is non-hardenable by heat treatment. In 304L, the carbon content has been lowered to .03% max. for corrosion resistance at heat affected zones from welding.

### Typical Applications

Architectural trim, beer barrels, cryogenic vessels, dairy equipment, and a wide variety of most food applications.

Typical Analysis	304	304L
Chrome	18.00-20.00	18.00-20.00
Nickel	8.00-11.00	8.00-11.00
Carbon	.08 max.	.03 max.
Manganese	2.0 max.	2.0 max.
Silicon	1.0 max.	1.0 max.
Molybdenum		
Other		
<b>Mechanical Properties</b>		<b>(Annealed)</b>
Brinell Hardness	170	160
Tensile-KSI	85	75
Yield-KSI	34	30
Elongation in 2"-%	60	60
Red. in Area-% Min	70	-
<b>Welding Characteristics</b>	Very good - tough welds	
<b>Machining</b> Compared to B1112 Screw Stock	45%	
<b>Specifications</b>		
AISI	<b>304 (Bar)</b>	<b>304L (Bar)</b>
ASTM	A276, A479, A580	A276,A479
AMS	5639	5647
QQS	763	763
AISI	<b>304 (Sheet)</b>	<b>304 (Plate)</b>
ASTM	A240	A240
AMS	5513	5513

## Grade 316L

316L is an austenitic chrome nickel steel with superior corrosion resistance to that of other chrome nickel steels. Widely used when exposed to chemical corrodents, as well as marine atmospheres. 316L is generally considered non-magnetic, but can become magnetic when cold worked. In 316L, the carbon content has been lowered to .03% max. for corrosion resistance at heat affected zones from welding.

### Typical Applications

Acetic acid compounds, kettles for cooking catsup, pulp and paper processing equipment, water softener tanks, and many marine applications.

Typical Analysis	316L
Chrome	16.00-18.00
Nickel	10.00-14.00
Carbon	.03 max.
Manganese	2.00 max.
Silicon	1.00 max.
Molybdenum	2.00-3.00
Other	
<b>Mechanical Properties</b>	<b>(Annealed)</b>
Brinell Hardness	160
Tensile-KSI	75
Yield-KSI	30
Elongation in 2"-%	60
Red. in Area-% Min	—
<b>Welding Characteristics</b>	Very good - tough welds
<b>Machining</b> Compared to B1112 Screw Stock	45%
<b>Specifications</b>	<b>316L (Bar)</b>
AISI	
ASTM	A276, A479, A580
AMS	5653
QQS	763
AISI	<b>316L (Sheet/Plate)</b>
ASTM	A240
AMS	5507

## Grade 409

409 is a general purpose stainless steel with 11% chromium. 409 is especially useful for applications requiring oxidation or corrosion protection beyond the capability of carbon steel and some coated steels. 409 has good oxidation resistance and formability, but lower corrosion resistance due to the chromium content. 409 is not as corrosion resistant as 304, 430 or 439 grades, but far superior to mild carbon steel. 409 can be formed by roll forming, stretch bending, deep drawing or pressing.

### Typical Applications

Automotive exhaust system applications such as manifolds, exhaust pipes, catalytic converters, mufflers, tail pipes and other components. Non automotive exhaust applications such as home heating systems, automotive thermostats and fuel filters, electrical transformer cases, caskets and heat exchanger tubing.

Typical Analysis	409
Chrome	10.50 - 11.70
Nickel	0.50
Carbon	0.030
Manganese	1.00
Silicon	1.00
Molybdenum	-
Other	-
<b>Mechanical Properties</b>	
Brinell Hardness	≤ 88 (179)
Tensile-KSI	55 (380)
Yield-KSI	25 (170)
Elongation in 2"-%	≥ 20
Red. in Area-% Min	-
<b>Welding Characteristics</b>	Successful in TIG-laser, HF, MIG and Spot Welding
<b>Machining</b> Compared to B1112 Screw Stock	
<b>Specifications</b>	
AISI	
ASTM	A240
AMS	
QQS	
AISI	
ASTM	
AMS	

## Grade 410

410 is a martensitic stainless steel that is air or oil hardened and responds well to hardening and tempering operations. Considered a 12% chromium steel, it offers superb combinations of strength and toughness depending on degree of heat treatments. In the annealed condition, it is a ready choice for forming and cold heading.

### Typical Applications

Machined parts, pump shafts, bushings, mining machinery, screws, valves, cutlery, oil burner parts and hardware.

Typical Analysis	410
Chrome	11.5-13.5
Carbon	.15 max.
Manganese	1.00 max.
Phosphorus	.040 max.
Sulphur	.025 max.
Silicon	1.00 max.
<b>Mechanical Properties</b>	<b>(Annealed)</b>
Brinell Hardness	185
Tensile—KSI	95
Yield—KSI	65
Elongation in 2"-%	30
Red. in Area-% Min	70
<b>Welding Characteristics</b>	Can be readily welded Pre-heat recommended
<b>Machining</b> Compared to B1112 Screw Stock	54%
<b>Specifications</b>	
AISI	410
ASTM	A193, A194, A276, A314, A479
AMS	5612, 5613

## Grade 416

416 is a martensitic chromium steel to which elements have been added to enhance the machinability. 416 is the most readily machinable of all the stainless steels and is suitable for use in automatic screw machines. 416 is less corrosion resistant than the chrome-nickel steels. It is magnetic in all conditions.

### Typical Applications

Aircraft fittings, bolts, nuts, studs, rivets, screws, many nonseizing and nongalling applications.

Typical Analysis	416
Chrome	12.00-14.00
Nickel	
Carbon	.15 max.
Manganese	1.25 max.
Silicon	1.00 max.
Molybdenum	.06 max.
Sulphur	.15 min.
<b>Mechanical Properties</b>	<b>(Annealed)</b>
Brinell Hardness	155
Tensile-KSI	75
Yield-KSI	40
Elongation in 2"-%	30
Red. in Area-% Min	60
<b>Welding Characteristics</b>	Poor brittle welds
<b>Machining</b> Compared to B1112 Screw Stock	90%
<b>Specifications</b>	<b>416 (Bar)</b>
AISI	416
ASTM	A581, A582
AMS	5610



## Grade 420

420 is a martensitic chrome steel capable of hardening to a maximum of approximately 500 Brinell. It has its optimum corrosion resisting qualities in the hardened and tempered condition. 420 is magnetic in all conditions.

### Typical Applications

Flatware knife blades, glass molds, hand tools, vegetable choppers.

Typical Analysis	420
Chrome	12.00-14.00
Carbon	.15 min.
Manganese	1.0 max.
Silicon	1.0 max.
Molybdenum	
Other	
Mechanical Properties	(Annealed)
Brinell Hardness	195
Tensile-KSI	95
Yield-KSI	50
Elongation in 2"-%	25
Red. in Area-% Min	55
Welding Characteristics	Fair - Preheat 400°-500° Anneal at 1300° after welding
Machining	
Compared to B1112 Screw Stock	54%
Specifications	420 (Bar)
AISI	420
ASTM	A276
AMS	5621
QQS	763

## Grade 430

430 stainless steel has good corrosion resistance combined with good formability. 430 is very similar to 439 grade stainless steel with slightly less chromium at 16% minimum content. 430 is more oxidation resistant and corrosion resistant than 409 grade. 430 is a popular non-hardenable grade most commonly used in indoor environments. 430 is readily cold formed by bending, deep drawing and stretch forming. 430 is relatively easy to machine and is comparable to that of structural carbon steel requiring the same recommendations regarding tooling, cutting speeds and cutting feeds. 430 can be welded although it may require annealing.

### Typical Applications

Appliances, food equipment, automotive, flue liners and roofing.

Typical Analysis	430
Chrome	14.00 - 18.00
Carbon	.12 max.
Nickel	
Manganese	1.0 max.
Silicon	1.0 max.
Molybdenum	
Other	
<b>Mechanical Properties</b>	<b>(Annealed)</b>
Brinell Hardness	155
Tensile—KSI	75
Yield—KSI	45
Elongation in 2"—%	30
Red. in Area—% Min	65
<b>Welding Characteristics</b>	Fair - Brittle welds Slight response to annealing
<b>Machining</b> Compared to B1112 Screw Stock	54%
<b>Specifications</b>	<b>430 (Sheet/Plate)</b>
AISI	430
ASTM	A176
AMS	5503

## Grade 439

439 stainless steel has good corrosion resistance due to its 17% minimum chromium content. 439 can be formed using a wide range of roll forming or mild stretch bending operations as well as more common drawing and bending operations. Special adjustment to chemical composition give this alloy excellent formability. 439 is more oxidation resistant and corrosion resistant than 409 grade. 439 has high thermal conductivity and low thermal expansion.

### Typical Applications

Automotive exhaust components, heating units and evaporator tubes.

Typical Analysis	439
Chrome	17.00 - 19.00
Carbon	0.030
Nickel	0.50
Manganese	1.00
Silicon	1.00
Molybdenum	
Other	
<b>Mechanical Properties</b>	<b>(Annealed)</b>
Brinell Hardness	≤ 89 (183)
Tensile—KSI	60 (415)
Yield—KSI	30 (205)
Elongation in 2"—%	≥ 22
Red. in Area-% Min	-
<b>Welding Characteristics</b>	Prone to grain growth in heat affected zone of weldment = poor tensile, fatigue and toughness in welded area.
<b>Machining</b> Compared to B1112 Screw Stock	
<b>Specifications</b>	<b>439 (Sheet)</b>
AISI	439
ASTM	A240
AMS	

## Grade 440C

440C is a martensitic chrome steel that is capable of acquiring, upon heat treatment, the highest hardness of any type of corrosion resisting steels. It has its optimum corrosion resisting qualities in the hardened and tempered condition and is magnetic in all conditions.

### Typical Applications

Instrument bearings, nozzles, steel balls and seats for oil well pumps, valve parts.

Typical Analysis	440C
Chrome	16.00-18.00
Nickel	
Carbon	.95-1.20
Manganese	1.0 max.
Silicon	1.0 max.
Molybdenum	.75 max.
Other	
<b>Mechanical Properties</b>	<b>(Annealed)</b>
Brinell Hardness	230
Tensile–KSI	110
Yield–KSI	65
Elongation in 2"-%	14
Red. in Area-% Min	25
<b>Welding Characteristics</b>	Not recommended
<b>Machining</b> Compared to B1112 Screw Stock	30%
<b>Specifications</b>	<b>440C (Bar)</b>
AISI	440C
ASTM	A276, A580
AMS	5630
QQS	763

## Grade 17-4 PH (630)/17-4 G&P/17-4 H900 G&P

17-4 is a martensitic precipitation hardening (maraging) steel that combines high strength and hardness with excellent corrosion resistance. A simple one-step aging treatment in the range of 900 to 1150 degrees hardens the alloy to its design strength levels.

### Typical Applications

High strength fittings, valves, bolts, shafting, pump parts, medical instruments.

Typical Analysis		17-4, 17-4 G&P, 17-4 H900 G&P					
Chrome		15.00-17.50					
Nickel		3.00-5.00					
Carbon		.07 max.					
Manganese		1.00 max.					
Silicon		1.00 max.					
Molybdenum							
Copper		3.00-5.00					
<b>Mechanical Properties</b>		<b>(Solution Treated)</b>					
Brinell Hardness		332					
Tensile–KSI		160					
Yield–KSI		145					
Elongation in 2"-%		15					
Red. in Area-% Min		55					
<b>Welding Characteristics</b>							
<b>Machining</b> Compared to B1112 Screw Stock		45%					
<b>Specifications</b>		<b>17-4 (Bar)</b>					
AISI		S17400					
ASTM		A564					
AMS		5643					
QQS		-					
Hardness Properties				17-4, 17-4 G&P, 17-4 H900 G&P			
Code	UTS min (kis)	YS min (kis)	EI min (%)	RA min (%)	Hardness min HRC / HB	Hardness max HRC / HB	Charpy min (ft-lb)
H925	170	155	10	44	38 / 375	45 / 429	5
H1025	155	145	12	45	35 / 331	42 / 401	15
H1050	155	145	13	45	32 / 311	38 / 375	15
H1075	145	125	13	45	32 / 311	38 / 375	20
H1100	140	115	14	45	31 / 302	37 / 363	25
H1150	135	105	16	50	28 / 277	37 / 352	30
H1150M	115	75	18	55	24 / 255	---	55
H1150D	125	105	16	50	24 / 255	33 / 311	30

## Stainless Rounds

### Standard Lengths: 12 foot random

AISI	303, 303 G&P	304/304L	316L , 316L BSQ	416, 416 PSQ
	17-4 PH	17-4 G&P	17-4 H900	410
	420	440C		

Size	Weight (lbs./ft.)	Size	Weight (lbs./ft.)	Size	Weight (lbs./ft.)	Size	Weight (lbs./ft.)
1/16	.010	1-1/8	3.379	2-5/8	19.322	6-1/2	117.584
3/32	.023	1-3/16	3.766	2-11/16	20.248	6-3/4	127.532
1/8	.042	1-1/4	4.173	2-3/4	21.181	7	136.987
5/32	.065	1-5/16	4.600	2-13/16	22.150	7-1/4	146.780
3/16	.094	1-3/8	5.049	2-7/8	23.125	7-1/2	156.911
7/32	.128	1-7/16	5.518	2-15/16	24.121	7-3/4	167.380
1/4	.167	1-1/2	6.008	3	25.155	8	178.187
9/32	.211	1-9/16	6.520	3-1/8	27.270	8-1/2	201.935
5/16	.261	1-5/8	7.051	3-1/4	29.470	9	225.981
11/32	.316	1-11/16	7.604	3-3/8	31.756	9-1/2	251.379
3/8	.376	1-3/4	8.178	3-7/16	32.941	10	278.129
13/32	.441	1-13/16	8.773	3-1/2	34.128	11	335.685
7/16	.511	1-7/8	9.388	3-5/8	36.824	12	398.651
15/32	.587	1-15/16	10.024	3-3/4	39.375	13	468.698
1/2	.668	2	10.681	4	44.731	14	542.609
9/16	.845	2-1/16	11.879	4-1/4	50.429	15	621.928
5/8	1.043	2-1/8	12.607	4-1/2	56.468	16	708.669
11/16	1.262	2-3/16	13.357	4-3/4	63.166	18	884.603
3/4	1.502	2-1/4	14.117	5	69.905	20	1102.171
13/16	1.763	2-5/16	14.910	5-1/4	76.985	22	1331.376
7/8	2.044	2-3/8	15.712	5-1/2	83.074	24	1582.217
15/16	2.347	2-7/16	16.549	5-3/4	93.289		
1	2.670	2-1/2	17.393	6	100.428		
1-1/16	3.014	2-9/16	18.431	6-1/4	108.837		

Available in Ground & Polished -- (+/--.0005)

## Stainless Half-Rounds

### Type 304

Width (inches)	Height (inches)	Weight (lbs./ft.)
1/2	1/4	.334
5/8	5/16	.520
3/4	3/8	.751

## Stainless Squares

### Annealed & Cold Drawn

Standard Lengths: 12 foot random

AISI	303	304/304L	316L	416	17-4	420
Size (inches)	Weight (lbs./ft.)	Weight (lbs./12 ft.)	Size (inches)	Weight (lbs./ft.)	Weight (lbs./12 ft.)	
1/8	.054	.64	1	3.400	40.80	
3/16	.120	1.44	1-1/8	4.303	51.63	
1/4	.213	2.55	1-1/4	5.310	63.72	
5/16	.332	3.98	1-1/2	7.650	91.80	
3/8	.480	5.76	1-3/4	10.410	124.92	
7/16	.666	7.99	2	13.600	163.20	
1/2	.850	10.20	2-1/2	21.250	255.00	
9/16	1.076	12.91	3	31.030	372.36	
5/8	1.330	15.96	3-1/2	42.740	512.88	
3/4	1.910	22.92	4	54.450	653.40	
7/8	2.600	31.20	5	85.000	1020.00	

\*Squares 2-1/2" and under are typically CF products

\*All squares over 2-1/2" are HRAP products

## Stainless Hexagons

### Annealed & Cold Drawn

Standard Lengths: 12 foot random

AISI	303	304/304L	316L	416	
Size (inches)	Weight (lbs./ft.)	Weight (lbs./12 ft.)	Size (inches)	Weight (lbs./ft.)	Weight (lbs./12 ft.)
1/8	.046	.56	1-1/8	3.730	44.76
3/16	.104	1.24	1-3/16	4.152	49.82
1/4	.184	2.21	1-1/4	4.600	55.20
5/16	.288	3.45	1-5/16	5.080	60.96
3/8	.414	4.97	1-3/8	5.570	66.84
7/16	.564	6.77	1-1/2	6.630	79.56
1/2	.736	8.83	1-5/8	7.775	93.24
9/16	.932	11.18	1-3/4	9.026	108.31
5/8	1.150	13.80	1-7/8	10.360	124.32
11/16	1.393	16.72	2	11.780	141.36
3/4	1.660	19.92	2-1/4	14.920	179.04
13/16	1.940	23.28	2-3/8	16.610	199.32
7/8	2.250	27.00	2-1/2	18.400	220.80
15/16	2.590	31.08	2-3/4	22.290	267.41
1	2.950	35.40	3	26.530	318.36
1-1/16	3.324	39.89			

## Stainless Flats

Hot Rolled Annealed, Pickled, True Mill Bar, Cold Drawn (303 only), Processed Plate Flat\*, or Sheared and Edged

Standard Lengths: 12 foot

AISI	303	304/304L	316L	17-4	17-4 H1150	420
------	-----	----------	------	------	------------	-----

"L" grade sizes available upon request.

Size (inches)	(lbs./ft.)	Size (inches)	(lbs./ft.)	Size (inches)	(lbs./ft.)
<b>1/8 x</b>	3/4 .326	<b>3/8 x</b>	1/2 .653	<b>3/4 x</b>	1 2.550
	1 .435		3/4 .979		1-1/4 3.190
	1-1/4 .544		1 1.305		1-1/2 3.830
	1-1/2 .653		1-1/8 1.468		1-3/4 4.88
	1-3/4 .761		1-1/4 1.630		2 5.100
	2 .870		1-1/2 1.956		2-1/2 6.380
	2-1/2 1.090		1-3/4 2.284		3 7.650
	3 1.310		2 2.550		3-1/2 8.930
	3-1/2 1.489		2-1/2 3.263		4 10.200
	4 1.740		3 3.915		5 12.750
	6 2.610		3-1/2 4.800		6 15.300
<b>3/16 x</b>	3/4 .489		4 5.220	<b>1x</b>	1-1/4 4.250
	1 .653		5 6.505		1-1/2 5.100
	1-1/4 .816		6 7.830		1-3/4 6.000
	1-1/2 .979		8 10.440		2 6.800
	1-3/4 1.150	<b>1/2 x</b>	3/4 1.305		2-1/2 8.500
	2 1.305		1 1.740		3 10.200
	2-1/2 1.630		1-1/4 2.175		3-1/2 11.900
	3 1.960		1-1/2 2.610		4 13.600
	3-1/2 2.160		1-3/4 2.975		5 17.000
	4 2.610		2 3.480		6 20.400
	5 3.260		2-1/2 4.350	<b>1-1/4 x</b>	1-1/2 6.490
	6 3.910		3 5.220		2 8.500
<b>1/4 x</b>	3/4 .638		3-1/2 6.090		2-1/2 10.630
	1 .870		4 6.960		3 12.750
	1-1/4 1.088		5 8.700		4 17.670
	1-1/2 1.305		6 10.440		6 25.520
	1-3/4 1.488		8 13.420	<b>1-1/2 x</b>	2 10.200
	2 1.740	<b>5/8 x</b>	3/4 1.631		2-1/2 13.196
	2-1/4 1.913		1 2.130		3 15.300
	2-1/2 2.175		1-1/4 2.656		4 20.400
	3 2.610		1-1/2 3.188		6 30.600
	3-1/2 3.045		2 4.250	<b>2 x</b>	2-1/2 17.000
	4 3.480		2-1/2 5.313		3 20.400
	4-1/2 3.915		3 6.380		4 27.200
	5 4.350		3-1/2 7.438	<b>3 x</b>	4 40.800
	6 5.220		4 8.500		
	8 6.960		5 11.183		
<b>5/16 x</b>	1 1.088		6 13.419		
	2 2.291				

\* Weight per foot on Processed Plate Flats slightly higher and specifications would be plate specifications.



## Stainless Sheet

### Cold Rolled, Annealed & Pickled Finishes:

- 2B Paper Interleaved
- 2B Laser Film, 1 Side
- #4 Laser Film, 1 Side
- BA Laser Film, 1 Side
- #8 Laser Film, 1 Side

AISI

201

304

304L

316L

Gauge (Nom. Dec)	Size (inches)	Weight (lbs./sqft)	Approx. Weight Sheet
<b>7 ga</b> (.1874)	48 x 96	7.871	251.87
	48 x 120	7.871	314.80
	48 x 144	7.871	377.80
	60 x 96	7.871	314.84
	60 x 120	7.871	393.55
	60 x 144	7.871	472.26
	72 x 96	7.871	377.80
	72 x 120	7.871	472.26
	72 x 144	7.871	566.71
<b>8 ga</b> (.1644)	48 x 96	7.014	224.44
	48 x 120	7.014	280.56
	60 x 120	7.014	350.70
	60 x 144	7.014	420.84
<b>10 ga</b> (.1350)	36 x 96	5.670	136.08
	36 x 120	5.670	170.10
	48 x 96	5.670	181.44
	48 x 120	5.670	226.80
	48 x 144	5.670	272.16
	60 x 96	5.670	226.80
	60 x 120	5.670	283.50
	60 x 144	5.670	340.20
	72 x 96	5.670	272.16
	72 x 120	5.670	340.20
	72 x 144	5.670	408.24
<b>11 ga</b> (.1200)	36 x 96	5.050	121.20
	36 x 120	5.050	151.50
	36 x 144	5.050	181.80
	48 x 96	5.050	161.60
	48 x 120	5.050	202.00
	48 x 144	5.050	242.40
	60 x 96	5.050	202.00
	60 x 120	5.050	252.50
	60 x 144	5.050	303.00
	72 x 96	5.050	242.40
	72 x 120	5.050	303.00
	72 x 144	5.050	363.60

Gauge (Nom. Dec)	Size (inches)	Weight (lbs./sqft)	Approx. Weight Sheet	
<b>12 ga</b> (.1054)	36 x 96	4.420	106.08	
	36 x 120	4.420	132.60	
	36 x 144	4.420	159.12	
	48 x 96	4.420	141.44	
	48 x 120	4.420	176.80	
	48 x 144	4.420	212.16	
	60 x 96	4.420	176.80	
	60 x 120	4.420	221.00	
	60 x 144	4.420	265.20	
<b>12 ga</b> (.1054)	72 x 96	4.420	272.16	
	72 x 120	4.420	265.20	
	72 x 144	4.420	318.24	
	<b>13 ga</b> (.0900)	48 x 96	3.780	120.96
<b>13 ga</b> (.0900)	48 x 120	3.780	151.20	
	48 x 144	3.780	181.44	
<b>14 ga</b> (.075)	36 x 96	3.155	75.72	
	36 x 120	3.155	94.65	
	36 x 144	3.155	113.58	
	48 x 96	3.155	100.96	
	48 x 120	3.155	126.20	
	48 x 144	3.155	151.44	
	60 x 96	3.155	126.20	
	60 x 120	3.155	157.75	
	60 x 144	3.155	189.30	
	72 x 96	3.155	151.44	
	72 x 120	3.155	189.30	
	72 x 144	3.155	227.16	
	<b>16 ga</b> (.060)	36 x 96	2.520	60.48
		36 x 120	2.520	75.60
36 x 144		2.520	90.72	
48 x 96		2.520	80.64	
48 x 120		2.520	100.80	
48 x 144		2.520	120.96	
60 x 96		2.520	100.80	
60 x 120		2.520	126.00	
60 x 144		2.520	151.20	
72 x 96		2.520	120.96	
72 x 120		2.520	151.20	
72 x 144		2.520	181.44	

Special length sheets available by request, please inquire with your Alro sales representative.

## Stainless Sheet

### Cold Rolled, Annealed & Pickled Finishes:

- 2B Paper Interleaved • 2B Laser Film, 1 Side • #4 Laser Film, 1 Side
- BA Laser Film, 1 Side • #8 Laser Film, 1 Side

AISI	201	304	304L	316L
------	-----	-----	------	------

Gauge (Nom. Dec)	Size (inches)	Weight (lbs./sqft)	Approx. Weight Sheet
<b>18 ga</b> (.048)	36 x 96	2.020	48.48
	36 x 120	2.020	60.60
	36 x 144	2.020	72.72
	48 x 96	2.020	64.64
	48 x 120	2.020	80.80
	48 x 144	2.020	96.96
	60 x 96	2.020	80.80
	60 x 120	2.020	101.00
<b>20 ga</b> (.036)	36 x 96	1.512	36.28
	36 x 120	1.512	45.36
	36 x 144	1.512	54.43
	48 x 96	1.512	48.38
	48 x 120	1.512	60.48
	48 x 144	1.512	72.57
	60 x 96	1.512	60.48
	60 x 120	1.512	75.60
60 x 144	1.512	90.72	

Gauge (Nom. Dec)	Size (inches)	Weight (lbs./sqft)	Approx. Weight Sheet
<b>22 ga</b> (.030)	36 x 96	1.260	30.24
	36 x 120	1.260	37.80
	36 x 144	1.260	45.36
	48 x 96	1.260	40.32
	48 x 120	1.260	50.40
	48 x 144	1.260	60.48
	60 x 96	1.260	50.40
	60 x 120	1.260	63.00
<b>24 ga</b> (.024)	36 x 96	1.008	24.19
	36 x 120	1.008	30.24
	48 x 96	1.008	32.25
	48 x 120	1.008	40.32
	48 x 144	1.008	48.38
<b>26 ga</b> (.018)	36 x 96	.756	18.14
	36 x 120	.756	22.68
	48 x 96	.756	24.19
	48 x 120	.756	30.24
	48 x 144	.756	36.29

Special length sheets available by request, please inquire with your Alro sales representative.

## Stainless Sheet

### Cold Rolled, Annealed & Pickled Finishes:

- 2B Paper Interleaved • 2B Laser Film, 1 Side • #4 Laser Film, 1 Side
- BA Laser Film, 1 Side • #8 Laser Film, 1 Side

AISI	409-2D	430	439-2D
------	--------	-----	--------

Gauge (Nom. Decimal)	Size (inches)	Weight (lbs./sqft.)	Approx. Weight (lbs./sheet)
24 ga (.024)	48 x 96	1.008	32.25
	48 x 120	1.008	40.32
22 ga (.030)	48 x 96	1.260	40.32
	48 x 120	1.260	50.40
20 ga (.036)	48 x 96	1.512	48.38
	48 x 120	1.512	60.48
18 ga (.048)	48 x 96	2.020	64.64
	48 x 120	2.020	80.80
16 ga (.060)	48 x 96	2.520	80.64
	48 x 120	2.520	100.80
14 ga (.075)	48 x 96	3.155	100.96
	48 x 120	3.155	126.20
12 ga (.1054)	48 x 96	4.420	141.44
	48 x 120	4.420	176.80
11 ga (.1200)	48 x 96	5.050	161.60
	48 x 120	5.050	202.00

## Stainless Plate

### Hot Rolled, Annealed & Pickled

AISI	201	304	304L	316L
ASTM	A240	A240	A240	A240

Thickness (inches) (lbs./sqft.)	Width (inches)
3/16 (8.579)	48
	60
	72
	96
1/4 (11.162)	48
	60
	72
	96
5/16 (13.746)	48
	60
	72
	96
3/8 (16.496)	48
	60
	72
	96
1/2 (21.663)	48
	60
	72
	96
5/8 (26.831)	48
	60
	72
	96
3/4 (32.123)	48
	60
	72
	96

Thickness (inches) (lbs./sqft.)	Width (inches)
7/8 (37.290)	60
	96
	96
1 (42.665)	48
	60
	96
1-1/4 (53.000)	60
	96
1-1/2 (63.337)	60
	96
1-3/4 (73.670)	60
	96
2 (84.008)	60
	96
2-1/4 (94.777)	60
	96
2-1/2 (105.113)	60
	96
2-3/4 (115.427)	60
	96
3 (126.301)	60
	96
3-1/2 (149.327)	60
	96
4 (168.264)	60
	96

## Stainless Tread Plate

### Hot Rolled, Annealed & Pickled

AISI	304
ASTM	A793 Pattern B

Thickness (inches)	Width (inches)
1/8	48
3/16	48
	60

Thickness (inches)	Width (inches)
1/4	48
	60
3/8	48

## Stainless Angle

### Hot Rolled, Annealed & Pickled

### 20 - 24 foot Random Lengths

AISI	304	304L	316L
ASTM	A276	A276	A276
FEDERAL		QQS-763	

Size (inches)	Weight (lbs./ft.)
3/4 x 3/4 x 1/8	.590
1 x 1 x 1/8	.800
1 x 1 x 3/16	1.160
1 x 1 x 1/4	1.490
1-1/4 x 1-1/4 x 1/8	1.010
1-1/4 x 1-1/4 x 3/16	1.480
1-1/4 x 1-1/4 x 1/4	1.920
1-1/2 x 1-1/2 x 1/8	1.230
1-1/2 x 1-1/2 x 3/16	1.800
1-1/2 x 1-1/2 x 1/4	2.340
2 x 2 x 1/8	1.650
2 x 2 x 3/16	2.440
2 x 2 x 1/4	3.190
2 x 2 x 3/8	4.700
2-1/2 x 2-1/2 x 3/16	3.070
2-1/2 x 2-1/2 x 1/4	4.100
2-1/2 x 2-1/2 x 3/8	5.900

Size (inches)	Weight (lbs./ft.)
3 x 2 x 3/16	3.070
3 x 2 x 1/4	4.100
3 x 3 x 3/16	3.710
3 x 3 x 1/4	4.900
3 x 3 x 3/8	7.200
3 x 3 x 1/2	9.550
3-1/2 x 3-1/2 x 1/4	5.800
3-1/2 x 3-1/2 x 3/8	8.650
4 x 3 x 1/4	5.800
4 x 3 x 3/8	8.500
4 x 4 x 1/4	6.600
4 x 4 x 3/8	9.800
4 x 4 x 1/2	12.800
5 x 3 x 3/8	9.850
5 x 5 x 1/4	8.895
5 x 5 x 3/8	12.802
6 x 4 x 3/8	12.300
6 x 6 x 1/4	10.755
6 x 6 x 3/8	15.551

## Stainless Channel

Type 304/304L, Rolled or Extruded - 20 foot Random Lengths

ASTM	A276
ASME	A279
FEDERAL	QQS-763

Size (inches)	Weight (lbs./ft.)
1-1/2 x 3/4 x 1/8	1.200
2 x 1 x 3/16	2.650
2 x 1 x 1/4	3.080
3 x 1-3/8 x 3/16	3.533
3 x 1-1/2 x 3/16	3.703
3 x 1-1/2 x 1/4	4.784

Size (inches)	Weight (lbs./ft.)
4 x 1-3/4 x 1/4	6.055
4 x 2 x 1/4	6.484
5 x 2-1/2 x 1/4	8.200
6 x 1.90 x .343	8.300
6 x 3 x 1/4	10.140
8 x 4 x 3/8	20.000


## Stainless Channel Dimensions

Designation	Depth (inches)	Width (inches)	Thickness Web (inches)	Thickness Flange (inches)	Sectional Area (inches)**2	Weight (lbs./ft.)
C 15 x 50	15	3.716	0.716	0.650	14.7	50
C 15 x 40	15	3.520	0.520	0.650	11.8	40
C 15 x 33.9	15	3.400	0.400	0.650	9.96	33.9
C 12 x 30	12	3.170	0.510	0.501	8.82	30
C 12 x 25	12	3.047	0.387	0.501	7.35	25
C 12 x 20.7	12	2.942	0.282	0.501	6.09	20.7
C 10 x 30	10	3.033	0.673	0.436	8.82	30
C 10 x 25	10	2.886	0.526	0.436	7.35	25
C 10 x 20	10	2.739	0.379	0.436	5.88	20
C 10 x 15.3	10	2.600	0.240	0.436	4.49	15.3
C 9 x 20	9	2.648	0.448	0.413	5.88	20
C 9 x 15	9	2.485	0.285	0.413	4.41	15
C 9 x 13.4	9	2.433	0.233	0.413	3.94	13.4
C 8 x 18.75	8	2.527	0.487	0.390	5.51	18.75
C 8 x 13.75	8	2.343	0.303	0.390	4.04	13.75
C 8 x 11.5	8	2.260	0.220	0.390	3.38	11.5
C 7 x 14.75	7	2.299	0.419	0.366	4.33	14.75
C 7 x 12.25	7	2.194	0.314	0.366	3.6	12.25
C 7 x 9.8	7	2.090	0.210	0.366	2.87	9.8
C 6 x 13	6	2.157	0.437	0.343	3.83	13
C 6 x 10.5	6	2.034	0.314	0.343	3.09	10.5
C 6 x 8.2	6	1.920	0.200	0.343	2.40	8.2
C 4 x 5.4	4	1.584	0.184	0.296	1.59	5.4
C 4 x 4.5	4	1.584	0.125	0.296	1.32	4.5
C 3 x 6	3	1.596	0.356	0.273	1.76	6
C 3 x 5	3	1.498	0.258	0.273	1.47	5
C 3 x 4.1	3	1.410	0.170	0.273	1.21	4.1

## Stainless Beams

Type 304/304L - 20 foot Random Lengths

ASTM A276, ASME A279, Federal QQS-763



Shape	Web		Flange	
	d (inches)	t <sub>w</sub> (inches)	b <sub>f</sub> (inches)	t <sub>f</sub> (inches)
HR S 3 x 5.7	3.00	.170	2.330	.260
HR S 4 x 7.7	4.00	.193	2.663	.293
HR S 6 x 12.5	6.00	.232	3.332	.359

Laser Fused	Web		Flange	
	d (inches)	t <sub>w</sub> (inches)	b <sub>f</sub> (inches)	t <sub>f</sub> (inches)
LC W 6 x 12	6.03	.230	4.000	.280
LC W 6 x 15	5.99	.230	5.990	.260
LC W 6 x 20	6.20	.260	6.020	.365
LC W 8 x 15	8.11	.245	4.015	.315
LC W 8 x 18	8.14	.230	5.250	.330
LC W 8 x 31	8.00	.285	7.995	.435

## Stainless Ornamental Tubing

Type 304 Welded, Type 316L - 20 foot Random Lengths

ASTM: A-554 (Polished finish available upon request)

### Squares & Rectangles

Outside Dimension & Gauge	Wall (dec.-in.)	Weight (lbs./ft.)
<b>1/2" x 1/2"</b>		
16	.062	.389
<b>5/8" x 5/8"</b>		
16	.062	.510
<b>3/4" x 3/4"</b>		
18	.049	.469
16	.062	.610
14	.083	.763
11	.120	1.020
<b>1" x 1"</b>		
18	.049	.630
16	.062	.827
14	.083	1.035
11	.120	1.440
<b>1-1/4" x 1-1/4"</b>		
18	.049	.790
16	.062	1.048
14	.083	1.317
11	.120	1.844
7	.180	2.620

Outside Dimension & Gauge	Wall (dec.-in.)	Weight (lbs./ft.)
<b>1-1/2" x 1-1/2"</b>		
18	.049	0.970
16	.062	1.268
14	.083	1.610
11	.120	2.252
7	.180	3.630
1/4	.250	4.067
<b>1-3/4" x 1-3/4"</b>		
11	.120	2.660
<b>2" x 2"</b>		
16	.062	1.710
14	.083	2.140
11	.120	3.050
7	.180	4.320
1/4	.250	6.010
<b>2-1/2" x 2-1/2"</b>		
11	.120	3.880
7	.180	5.680
1/4	.250	7.343

## Stainless Ornamental Tubing

Type 304 Welded, Type 316L - 20 foot Random Lengths

ASTM: A-554 (Polished finish available upon request)

### Squares & Rectangles

Outside Dimension & Gauge	Wall (inches)	Weight (lbs/ft.)
<b>3" x 3"</b>		
14	.083	3.290
11	.120	4.970
7	.180	6.900
1/4	.250	9.350
<b>3-1/2" x 3-1/2"</b>		
1/4	.250	11.015
<b>4" x 4"</b>		
11	.120	6.450
7	.180	9.410
1/4	.250	12.680
3/8	.375	18.485
<b>5" x 5"</b>		
7	.180	11.799
1/4	.250	16.150
3/8	.375	23.588
<b>6" x 6"</b>		
7	.180	14.247
1/4	.250	18.770
3/8	.375	28.688
<b>8" x 8"</b>		
1/4	.250	26.350
3/8	.375	38.888
<b>1" x 1/2"</b>		
16	.062	.606
<b>1-1/2" x 1/2"</b>		
16	.062	.830
<b>1-1/2" x 3/4"</b>		
16	.062	.990
<b>1-1/2" x 1"</b>		
16	.062	1.048
11	.120	1.884
<b>2" x 1"</b>		
16	.062	1.269
11	.120	2.252
<b>2" x 1-1/2"</b>		
11	.120	2.660
<b>3 x 1</b>		
11	.120	3.070

Outside Dimension & Gauge	Wall (inches)	Weight (lbs/ft.)
<b>3" x 1-1/2"</b>		
14	.083	3.030
11	.120	3.480
7	.180	4.960
<b>3" x 2"</b>		
11	.120	3.884
7	.180	5.679
1/4	.250	7.100
<b>4" x 2"</b>		
11	.120	4.750
7	.180	6.903
1/4	.250	9.350
<b>4" x 3"</b>		
11	.120	5.516
7	.180	8.130
1/4	.250	11.024
<b>5" x 3"</b>		
1/4	.250	12.683
<b>6" x 2"</b>		
7	.180	9.270
1/4	.250	12.680
<b>6" x 3"</b>		
7	.180	10.520
1/4	.250	13.730
<b>6" x 4"</b>		
7	.180	11.900
1/4	.250	16.350
<b>8" x 2"</b>		
7	.180	11.900
1/4	.250	18.270
<b>8" x 4"</b>		
1/4	.250	18.770
3/8	.375	49.088
<b>8" x 6"</b>		
1/4	.250	22.910
<b>10" x 2"</b>		
1/4	.250	18.770

## Stainless Round Tube

Type 304 Welded, Type 316L Welded - 20 ft Random Lengths  
ASTM A554, Seamless ASTM A269

AISI	304	316L
------	-----	------

OD	Wall	lbs./foot
1/4	.028	.066
1/4	.035	.080
1/4	.049	.105
1/4	.065	.129
1/4	.083	.148
5/16	.028	.086
5/16	.049	.139
5/16	.065	.172
3/8	.028	.104
3/8	.035	.127
3/8	.049	.171
3/8	.065	.215
3/8	.083	.220
1/2	.035	.174
1/2	.049	.236
1/2	.065	.302
1/2	.083	.414
1/2	.095	.491
1/2	.120	.487
5/8	.035	.221
5/8	.049	.301
5/8	.065	.389
5/8	.120	.647
3/4	.035	.267
3/4	.049	.367
3/4	.065	.476
3/4	.083	.591
3/4	.120	.807
3/4	.188	.850
7/8	.049	.432
7/8	.065	.562
7/8	.120	.968
1	.035	.361
1	.049	.498
1	.065	.649
1	.083	.813
1	.120	1.128
1	.188	1.630
1	.250	2.004

OD	Wall	lbs./foot
1-1/4	.049	.629
1-1/4	.065	.823
1-1/4	.083	1.034
1-1/4	.120	1.467
1-1/4	.188	2.132
1-1/4	.250	2.670
1-1/2	.049	0.759
1-1/2	.065	0.996
1-1/2	.083	1.257
1-1/2	.120	1.770
1-1/2	.188	2.634
1-1/2	.250	3.338
1-5/8	.065	1.083
1-3/4	.065	1.170
1-3/4	.120	2.089
1-3/4	.188	3.136
1-3/4	.250	4.005
2	.049	1.021
2	.065	1.343
2	.120	2.409
2	.188	3.670
2	.250	4.673
2	.375	6.508
2-1/4	.065	1.530
2-1/4	.120	2.730
2-1/4	.188	4.140
2-1/4	.250	5.340
2-1/4	.375	
2-1/2	.065	1.683
2-1/2	.120	3.050
3	.065	2.030
3	.120	3.691
4	.065	2.732



## Stainless Welded Pipe

### 20 foot Random Lengths

AISI	304	316L		
ASTM	A312	A312		
Nominal Pipe Size	OD (inches)	ID (inches)	Wall Thickness	Weight (lbs./foot)
<b>Schedule 10</b>				
1/2	.840	.674	.083	.671
3/4	1.050	.884	.083	.857
1	1.315	1.097	.109	1.420
1-1/4	1.660	1.442	.109	1.806
1-1/2	1.900	1.682	.109	2.080
2	2.375	2.157	.109	2.638
2-1/2	2.875	2.635	.120	3.530
3	3.500	3.260	.120	4.332
4	4.500	4.260	.120	5.610
5	5.563	5.295	.134	7.840
6	6.625	6.357	.134	9.290
8	8.625	8.329	.148	13.400
10	10.750	10.420	.165	18.650
<b>Schedule 40</b>				
1/8	.405	.269	.068	.240
1/4	.540	.364	.088	.420
3/8	.675	.493	.091	.570
1/2	.840	.622	.109	.851
3/4	1.050	.824	.113	1.131
1	1.315	1.049	.133	1.680
1-1/4	1.660	1.380	.140	2.270
1-1/2	1.900	1.610	.145	2.720
2	2.375	2.067	.154	3.650
2-1/2	2.875	2.469	.203	5.850
3	3.500	3.068	.216	7.580
3-1/2	4.000	3.548	.226	9.110
4	4.500	4.026	.237	10.790
5	5.563	5.047	.258	14.620
6	6.625	6.065	.280	18.970
8	8.625	7.981	.322	28.550
10	10.750	10.020	.365	40.480
<b>Schedule 80</b>				
1/4	.540	.302	.119	.540
3/8	.675	.423	.126	.730
1/2	.840	.546	.147	1.090
3/4	1.050	.742	.154	1.470
1	1.315	.957	.179	2.170
1-1/4	1.660	1.278	.191	3.030
1-1/2	1.900	1.500	.200	3.630
2	2.375	1.939	.218	5.070
2-1/2	2.875	2.323	.276	7.660
3	3.500	2.900	.300	10.250
4	4.500	3.826	.337	14.980

## Stainless Bar Tolerances

### Rounds, Cold Finished (CF)

Drawn, Turned or Centerless Ground

Specified Size (inches)	Over (inches)	Under (inches)
1/8 up to 5/16	0.001	0.001
5/16 up to 1/2	0.0015	0.0015
1/2 up to 1	0.002	0.002
1 up to 1-1/2	0.0025	0.0025
1-1/2 up to 4	0.003	0.003

### Rounds, Rough Turned (RT)

Specified Size (inches)	Over (inches)	Under (inches)
over 2 to 2-1/2	0.031	0.000
over 2-1/2 to 3-1/2	0.046	0.000
over 3-1/2 to 4-1/2	0.062	0.000
over 4-1/2 to 5-1/2	0.078	0.000
over 5-1/2 to 6-1/2	0.125	0.000
over 6-1/2 to 8	0.156	0.000
over 8 to 12	0.187	0.000
over 12	0.218	0.000

## Stainless Rounds Straightness Tolerances

Hot Rolled	Cold Finished
1/8" in any 5' section of the bar	1/16" in any 5' section of the bar

## Stainless Hex and Squares (CF)

Specified Size (inches)	Over (inches)	Under (inches)
1/8 up to 5/16	0.000	0.002
5/16 up to 1/2	0.000	0.003
1/2 thru 1	0.000	0.004
Over 1 to 2	0.000	0.006
Over 2 to 3	0.000	0.008
Over 3	0.000	0.010
4 to 4-1/2	+ .0310 / +.0510	
4-1/2 to 6	+ .0310 / +.0650	
6 to 6-3/8	+ .0520 / +.0820	
6-3/8 to 6-5/8	+ .0520 / +.0930	
6-5/8 and up	+ .0625 / +.1250	

## Stainless Ground Bar Tolerances

Abbreviation	Description	Tolerance	Micro Finish	Straightness
CG	Centerless Ground	+/- Tolerance by size	45 RMS	.008" TIR/FT
G&P	Ground & Polished	+/- .0005"	32/20 RMS	.006" TIR/FT
PG	Precision Ground	+0/- .0005"	16 RMS	.006" TIR/FT
TG&P Stainless	Turned Ground & Polished	+/- .0005"	32 RMS	.006" TIR/FT
RT	Rough Turned	+ .032/-0"	125 RMS	.012" TIR/FT
	STN	Straightened	---	.008/.006" TIR/FT
P STN	Precision Straightened	---	---	.004" TIR/FT
BSQ	Bearing Shaft Quality	-.0005/- .0015"	32 RMS	.006" TIR/FT
PSQ -.500" -<1.500"	Pump Shaft Quality	+0/- .0015"	32/25 RMS	.0015" TIR/FT
PSQ -1.500" -4.000"	Pump Shaft Quality	+0/- .002"	32/25 RMS	.0015" TIR/FT
PSQ ->4.000" -5.000"	Pump Shaft Quality	+0/- .003"	32/25 RMS	.0015" TIR/FT

## Stainless Sheet Thickness Tolerances

Gauge	Nominal Decimal	Tolerance Plus/Minus
7	.1874	.007
8	.1650	.007
10	.1350	.006
11	.1200	.005
12	.1054	.005
13	.0900	.004
14	.0751	.004
16	.0595	.003
18	.0480	.003
19	.0420	.003
20	.0355	.002
22	.0293	.002
24	.0235	.0015
26	.0178	.0015
28	.0151	.0015

## Stainless Sheet Tolerances

### Flatness, Stretcher Level Flatness

Thickness (inches)	Width (inches)	Length (inches)	Flatness Tolerances
under 3/16	thru 48	up to 96	1/8
under 3/16	thru 48	over 96	1/4
under 3/16	over 48	thru 96	1/4
under 3/16	over 48	over 96	1/4

\*Flatness is defined as maximum deviation from a horizontal flat surface.

## Stainless Plate Tolerances

### Thickness Tolerance for Stainless and Heat Resisting Steels

Specified Thickness (inches)	Width (inches)	
	Thru 84	Over 84 thru 120
3/16 up to 3/8	+0.045 / -0.010	+0.050 / -0.010
3/8 up to 3/4	+0.055 / -0.010	+0.060 / -0.010
3/4 up to 1	+0.060 / -0.010	+0.065 / -0.010
1 up to 2	+0.070 / -0.010	+0.075 / -0.010
2 up to 3	+0.125 / -0.010	+0.150 / -0.010
3 up to 4	+0.175 / -0.010	+0.210 / -0.010
4 up to 6	+0.250 / -0.010	+0.300 / -0.010
6 up to 8	+0.350 / -0.010	+0.420 / -0.010
8 thru 10	+0.450 / -0.010	+0.540 / -0.010

## Flatness Tolerance for Annealed Stainless and Heat Resisting Steel Plate

Specified Thickness (inches)	Flatness Tolerance for Thickness & Widths				
	Width (inches)				
	Up thru 48	Over 48 up to 60	60 up to 72	72 up to 84	84 thru 96
3/16 up to 1/4	3/4	1-1/16	1-1/4	1-3/8	1-5/8
1/4 up to 3/8	11/16	3/4	15/16	1-1/8	1-3/8
3/8 up to 1/2	1/2	9/16	11/16	3/4	15/16
1/2 up to 3/4	1/2	9/16	5/8	5/8	13/16
3/4 up to 1	1/2	9/16	5/8	5/8	3/4
1 up to 1-1/2	1/2	9/16	9/16	9/16	11/16
1-1/2 up to 4	3/16	5/16	3/8	7/16	1/2
4 thru 6	1/4	3/8	1/2	9/16	5/8

\*Flatness is defined as maximum deviation from a horizontal flat surface.

## Stainless Flats Tolerances

### Sheared and Edged Flats

Order Thickness (inches)	Permitted Variation in Thickness (inches)		Permitted Variation <sup>A</sup> in Width (inches)			
	Over	Under	Width up to 4"		Widths Over 4"	
			Over	Under	Over	Under
1/8 Over 0.114 to 0.130	0.010	0.010	0.094	0.031	0.094	0.094
3/16 - 3/8	0.050	0.010	0.094	0.031	0.094	0.094
3/8 - 3/4	0.060	0.010	0.094	0.031	0.094	0.094

### True Bar Flats

True Bar  Width (inches)	Permitted Variations In Thickness For Thicknesses Given (inches)			Permitted Variations In Width Tolerance Over and Under (inches)	
	1/8 thru 1/2	Over 1/2 thru 1	Over 1 thru 2	Over	Under
Up thru 1	+/- .008	+/- .010	—	.015	.015
Over 1 thru 2	+/- .012	+/- .015	+/- .031	.031	.031
Over 2 thru 4	+/- .015	+/- .020	+/- .031	.062	.031
Over 4 thru 6	+/- .015	+/- .020	+/- .031	.093	.062
Over 6 thru 8	+/- .016	+/- .025	+/- .031	.125	.156
Over 8 thru 10	+/- .021	+/- .031	+/- .031	.156	.187

### True Bar Straightness Tolerances

HR	CF
1/8" in any 5 foot section of the bar	1/16" in any 5 foot section of the bar

## Stainless Angle Tolerances

Leg Tolerance (Length)	+/- 1/8"
Weight Tolerance	+/- 7-1/2%
Right Angle Tolerance	+/- 2°
Straightness or Camber	1/8" in 5'

## Stainless Channel Tolerances

### Section (Leg Tolerance)

Under 1" (Total).....	0.040
1" - 3" incl.....	0.062
3" - 4" incl.....	0.093
Over 4".....	0.125

**Angular** +/-2"

**Corner Radii** 1/4" or less

**Leg Radii** 1/4" or less

### Transverse Flatness


.010" per inch of width, .050" max.

### Length

Up to 12' incl.	
To 3" wide section	
Over 3" to 6" incl.	+ 3/16 / - 0
Over 6"	+ 1/4 / - 0
Over 12'	
To 3" wide section	+ 3/16 / - 0
Over 3" to 6" incl.	+ 1/4 / - 0
Over 6"	+ 5/16 / - 0

### Camber

Camber or bow tolerances shall not exceed 0.025 in. [0.60mm] x length in ft. [<sup>m</sup>/<sub>3</sub>]



### Twist

Width of Section	Rise in 5 ft.
1/2" to 1-1/2" incl.	.125"
Over 1-1/2" to 4" incl.	.188"
Over 4"	.250"

## Stainless Round Tube Tolerances

Normal Round (inches)	Wall Thickness (inches)	O.D. Tolerance (inches)	Wall Tolerance (%)
5/8 to 1 incl	0.035 to 0.062	+ or - 0.005	+ or - 10%
5/8 to 1 incl	Over 0.062	+ or - 0.010	+ or - 10%
Over 1 to 1-1/2 incl	0.035 to 0.062	+ or - 0.008	+ or - 10%
Over 1 to 1-1/2 incl	Over 0.062	+ or - 0.010	+ or - 10%
Over 1 to 2-1/2 incl	Over 0.035	+ or - 0.012	+ or - 10%
Over 2-1/2 to 3-1/2 incl	Over 0.049	+ or - 0.020	+ or - 10%
Over 3-1/2 to 5 incl	Over 0.049	+ or - 0.025	+ or - 10%
Over 5	Over 0.083	+ or - 0.030	+ or - 10%

## Stainless Square & Rectangular Tube Tolerances

Largest Nominal Outside Diameter (inches)	O.D. Tolerance Concavity or Convexity (inches)	Wall Tolerance (%)
To 1-1/4 incl.	+ or - 0.015	+ or - 10%
Over 1-1/4 to 2-1/2 incl.	+ or - 0.020	+ or - 10%
Over 2-1/2 to 5-1/2 incl.	+ or - 0.030	+ or - 10%
Over 5-1/2	+ or - 0.060	+ or - 10%