



The lightweight cutting board for large applications that must weigh less than 50 pounds to conform to regulations

King CuttingBoard XL is an exceptionally white natural polyethylene color, creating a bright, clean, sanitary look that commercial food processing operations require.

The sheets are approximately 30% lighter in weight than standard King CuttingBoard®, allowing for easy handling and cleanup. Bacteria, odors and cleaning fluids wash completely off. King CuttingBoard XL will not dull knives like wood. King CuttingBoard XL is tested and certified by the NSF and the material is FDA approved. It is made to last in the most demanding commercial environments. It is easy to clean, easy to maintain, and will not splinter or rot.

KING
CUTTINGBOARD[®] XL

Applications

- Commercial Cutting Boards
- Consumer Cutting Boards



Specifications

Standard Sheet Sizes

in: 60" x 96"

mm: 1524mm x 2438.5mm

in: 60" x 120"

mm: 1524mm x 3048mm

Standard Gauges

in: 1/4" | 1/2" | 3/4" | 1"

mm: 6.35mm | 12.7mm | 19.05mm | 25.4mm

Approximate Weight 60" x 96"

lbs: 40 lbs | 80 lbs | 120 lbs | 160 lbs

kg: 18.14kg | 36.29kg | 54.43kg | 72.57kg

Approximate Weight 60" x 120"

lbs: 50 lbs | 100 lbs | 150 lbs | 200 lbs

kg: 22.67kg | 45.36kg | 60kg | 90.72kg

Tolerance information: Gauges 1/4" up to 1" ± 5%
Length and width plus only at room temperature

Custom sheet sizes and gauges available

Standard Color



Natural

*Note: Color accuracy can vary considerably on computer monitors and printers.
Please consult your distributor for a product sample before making critical color choices.

| Properties | Units | ASTM | Nominal Values |
|-----------------------------------|-------------------|-------|----------------|
| Density | g/cm ³ | D792 | 0.77 & 0.7187 |
| Tensile Strength @ Yield | psi | D638 | >3,300 |
| Tensile Modulus | psi | D638 | 165,000 |
| Elongation @ Yield | % | D638 | 9.6 |
| Flexural Modulus | psi | D790 | 130,000 |
| Flexural Stress @ 5% Strain | psi | D790 | 2,990 |
| Compressive Properties 10% Strain | psi | D695 | 2,910 |
| Durometer | Shore D | D2240 | 64.9 |
| Izod Impact Resistance | ft.lbs./in.2 | D256 | 1.4 |
| Heat Deflection Temp. 66 psi | °C (°F) | D648 | 87°C (188°F) |
| Screw Holding Strength | lbs | D1761 | 325 |

*All values are determined on specimens prepared according to ASTM standards.

Nominal values should not be interpreted as specifications.

King CuttingBoard® XL is made entirely from FDA and made with USDA approved materials.

King CuttingBoard® XL is NFS approved for Standards 2 & 51.



King Plastic Corporation
Our Innovation. Your Imagination.®

1100 N. Toledo Blade Blvd. | North Port, FL 34288 USA
P: 941.493.5502 | F: 941.497.3274 | www.kingplastic.com